

Certificate of Analysis

IARM NiN155-18

Nickel Alloy, N-155 / R30155

Certified Reference Material

Certified Values listed in wt.% with associated uncertainties

Al	0.153 ± 0.008	B	0.0024 ± 0.0004	C	0.116 ± 0.003	Co	19.2 ± 0.1
Cr	20.9 ± 0.2	Cu	0.039 ± 0.002	Fe	31.4 ± 0.3	Mn	1.46 ± 0.02
Mo	2.87 ± 0.03	N	0.12 ± 0.01	Nb	1.00 ± 0.02	Ni	20.1 ± 0.2
P	0.008 ± 0.001	Si	0.55 ± 0.01	Ti	0.0026 ± 0.0006	V	0.0236 ± 0.0008
W	2.42 ± 0.03	Zr	0.0057 ± 0.0009				

Indicative Values listed in ppm

H (4)	Mg (8)	O (10)	Re (<100)	S (9)	Sn (<50)	Ta (10)
-------	--------	--------	-----------	-------	----------	---------

Description and Intended Use

This **Certified Reference Material** is covered under the scope of accreditation to **ISO 17034** by LGC Standards - Manchester, NH. As an ISO 17034 certified reference material, appropriate use of this material will fulfill the certified reference material and traceability requirements for use in **ISO 17025** certified laboratories. This CRM may come in the form of a solid disk, chips, or powder. The intended use of this CRM may include, but is not limited to, the calibration of instruments and the validation of analytical methods.

Instructions for Use

1. The test surface is on the opposite side of the labeled surface, which includes the material identification. The entire thickness of the unit is certified. However, the user is cautioned not to measure disks less than 2 mm thick when using X-ray fluorescence spectrometry. Each packaged disk has been prepared by finishing the test surface using a lathe. The user must determine the correct surface preparation procedure for each analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing, as these processes may contaminate the surface.
2. The minimum sample size for chips should be individually evaluated based on the analytical technique used; this would typically be greater than 0.1 grams.
3. The material should be stored in a cool, dry location when not in use.
4. Chips are not recommended for gas analysis.

The following data represents all pertinent information reported as it applies to the chemical characterization of this material.

	Al	B	C	Co	Cr	Cu	Fe	H	Mg	Mn	Mo	N	Nb	Ni	O	P
1	0.1393	0.0018	0.1043	18.93	20.33	0.0336	31.00	0.0004	0.0006	1.410	2.780	0.0942	0.9630	19.60	0.0003	0.0044
2	0.1410	0.0020	0.1150	19.00	20.68	0.0340	31.01		0.0007	1.426	2.810	0.0960	0.9695	19.64	0.0007	0.0055
3	0.1420	0.0023	0.1150	19.00	20.69	0.0370	31.20		0.0008	1.446	2.844	0.1153	0.9700	19.80	0.0015	0.0066
4	0.1422	0.0024	0.1160	19.07	20.72	0.0370	31.38		0.0008	1.450	2.850	0.1200	0.9860	19.96	0.0018	0.0073
5	0.1460	0.0024	0.1160	19.08	20.73	0.0375	31.53		0.0008	1.452	2.857	0.1218	0.9950	19.97		0.0080
6	0.1470	0.0024	0.1163	19.30	20.91	0.0380	31.70		0.0009	1.461	2.860	0.1230	1.0100	19.97		0.0081
7	0.1490	0.0027	0.1200	19.32	20.96	0.0389	31.74		<0.0005	1.462	2.888	0.1260	1.0131	20.06		0.0083
8	0.1498	0.0035	0.1200	19.33	21.00	0.0397	31.85		≤0.005	1.470	2.890	0.1440	1.0170	20.26		0.0087
9	0.1500		0.1203	19.36	21.06	0.0400			≤0.005	1.473	2.890		1.0200	20.30		0.0089
10	0.1520		0.1205	19.43	21.08	0.0400				1.480	2.892		1.0220	20.43		0.0093
11	0.1680			19.43	21.10	0.0413				1.482	2.893		1.0366	20.54		0.0100
12	0.1770				21.36	0.0427				1.482	2.926			20.60		
13	0.1792				21.54	0.0432				1.520	2.950					
14																
15																
Mean	0.1525	0.0024	0.1163	19.21	20.94	0.0387	31.43	0.0004	0.0008	1.463	2.872	0.1175	1.0002	20.09	0.0011	0.0077
STDV.	0.0135	0.0005	0.0048	0.189	0.316	0.0029	0.331		0.0001	0.028	0.045	0.0162	0.0249	0.333	0.0007	0.0017
Certified	0.153	0.0024	0.116	19.2	20.9	0.039	31.4	(0.0004)	(0.0008)	1.46	2.87	0.12	1.00	20.1	(0.001)	0.008
U _{CRM}	0.008	0.0004	0.003	0.1	0.2	0.002	0.3			0.02	0.03	0.01	0.02	0.2		0.001
Methods	I,X,IM,O	I,IM	C,O	I,X,O	I,X,O	I,X,IM,O	I,X,O	F	I,X,IM	I,X,IM,O	I,X,IM,O	F,C	I,X,O	I,X,O	F	IM,I,X,O

	Re	S	Si	Sn	Ta	Ti	V	W	Zr							
1	0.0003	0.0004	0.5300	0.0018	0.0004	0.0010	0.0220	2.337	0.0031							
2	0.0180	0.0004	0.5366	<0.005	0.0006	0.0020	0.0230	2.369	0.0047							
3	<0.00005	0.0006	0.5385	≤0.005	0.0014	0.0024	0.0230	2.378	0.0050							
4	<0.0001	0.0008	0.5405	≤0.005	0.0017	0.0026	0.0235	2.389	0.0054							
5	<0.01	0.0010	0.5440		0.0027	0.0026	0.0237	2.391	0.0060							
6	<0.01	0.0022	0.5440		<0.00005	0.0026	0.0243	2.397	0.0060							
7		<0.0005	0.5490		<0.0005	0.0028	0.0245	2.410	0.0060							
8		≤0.005	0.5490		<0.005	0.0034	0.0249	2.422	0.0063							
9		≤0.005	0.5560		≤0.005	0.0036	≤0.005	2.430	0.0068							
10			0.5697			≤0.005	≤0.005	2.439	0.0079							
11			0.5730			≤0.005		2.440	≤0.005							
12			0.5821			≤0.005		2.510								
13								2.530								
14																
15																
Mean	0.0092	0.0009	0.5510	0.0018	0.0014	0.0026	0.0236	2.419	0.0057							
STDV.	0.0125	0.0007	0.0161		0.0009	0.0008	0.0010	0.054	0.0013							
Certified	(<0.01)	(0.0009)	0.55	(<0.005)	(0.001)	0.0026	0.0236	2.42	0.0057							
U _{CRM}			0.01			0.0006	0.0008	0.03	0.0009							
Methods	I,IM	C,X,O	I,X,W,O	I,X	I,X,IM	I,X,IM,O	I,X,IM,O	I,X,O	IM,X,I							

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, IM=ICP-MS, D = DC Arc, O = AES, X = XRF, G = GDAES or GDMS, H = Hollow Cathode AES

Certification Laboratories

Sheffield Assay Office
Massachusetts Materials Research
Connecticut Metallurgical, Inc.
IMR Test Labs
LGC Standards

Sheffield, UK
West Boylston, MA
East Hartford, CT
Lansing, NY
Manchester, NH

Scrooby's Laboratory Service
Laboratory Testing, Inc.
Dirats Laboratories
NSL Analytical Services
EAG Laboratories

Rynfield, South Africa
Hatfield, PA
Westfield, MA
Cleveland, OH
Liverpool, NY

Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognized reference materials. Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

Homogeneity and Uncertainty

"Uncertainty" values, as reported adjacent to certified concentration values, are based on a 95% Confidence Interval. These estimated uncertainties include the combined effects of method imprecision, material inhomogeneity, and any bias between methods. Homogeneity data from experimental XRF results are reflected in both the overall statistics and certified data. Homogeneity samples are selected by a systematic sampling procedure. The number of samples may be determined by equation 1, where N_{prod} is the number of units produced and N_{min} is the number of samples used for homogeneity testing. These samples are arranged in a simple randomized design such that each sample is analyzed multiple times by XRF. Homogeneity may also be determined within sample using an applied version of ASTM E826. A single factor ANOVA is used to calculate uncertainty due to inhomogeneity (U_{hom}). Uncertainty of the material is calculated by equation 2, where $H=U_{hom}$, S = Standard deviation, t = t-value at 95% CI, and n = number of observations.

$$1. N_{min} = \max(10, \sqrt[3]{N_{prod}})$$

$$2. U_{CRM} = \frac{\sqrt{H^2 + S^2}}{\sqrt{n}} * t$$

Expiration

The certification of this material is valid indefinitely, within the uncertainty specified, provided the material is handled and stored in accordance with the instructions stated on this certificate. The certification is nullified if the material is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.



Kimberly Halkiotis, Global Product Manager
ARMI | MBH - LGC Standards Industrial Sector



ISO 17034 Accredited: Reference Materials
Producer, Certificate # 2848.02
ISO/IEC 17025 Accredited: Chemical Testing,
Certificate # 2848.01