

**Certified Reference Material**

**Certificate of Analysis**

**Product ID:** MBH-32X PB17 A

ISO  
17034:2016

ISO/IEC  
17025:2017

ISO  
9001:2015

Revision No.: 000  
Revision Date: 03/01/2022

**Product Description:** Copper Alloy, Phosphor-Copper

**Description and Intended Use:** This **Certified Reference Material** is covered under the scope of accreditation to **ISO 17034** by LGC Standards - Manchester, NH. As an ISO 17034 certified reference material, appropriate use of this material will fulfill the certified reference material and traceability requirements for use in **ISO 17025** accredited laboratories. This CRM may come in the form of a solid disk, or chips. The intended use of this CRM may include, but is not limited to, the calibration of instruments and the validation of analytical methods.

**Certified Values listed in wt.% with associated uncertainties**

<b>Ag</b> 0.017 ± 0.002	<b>As</b> 0.175 ± 0.005	<b>Bi</b> 0.026 ± 0.004	<b>Cd</b> 0.0004 ± 0.0004
<b>Co</b> 0.0018 ± 0.0002	<b>Cr</b> 0.0004 ± 0.0003	<b>Cu</b> 77.3 ± 0.3	<b>Fe</b> 0.0009 ± 0.0004
<b>Ni</b> 0.044 ± 0.003	<b>P</b> 0.017 ± 0.002	<b>Pb</b> 0.213 ± 0.005	<b>S</b> 0.0220 ± 0.0009
<b>Sb</b> 0.051 ± 0.003	<b>Se</b> 0.0022 ± 0.0004	<b>Sn</b> 21.8 ± 0.3	<b>Zn</b> 0.0188 ± 0.0006

**Indicative Values listed in ppm**

Al (20)	Au (<5)	Ge (<10)	Mg (50)	Mn (<4)	Nb (2)	O (<70)
Si (7)	Zr (2)					

**Homogeneity and Uncertainty:** "Uncertainty" values, as reported adjacent to certified concentration values, are based on a 95% Confidence Interval. These estimated uncertainties include the combined effects of method imprecision, material inhomogeneity, and any bias between methods. Homogeneity data from experimental XRF results are reflected in both the overall statistics and certified data. Homogeneity samples are selected by a systematic sampling procedure. The number of samples may be determined by equation 1, where  $N_{prod}$  is the number of units produced and  $N_{min}$  is the number of samples used for homogeneity testing. These samples are arranged in a simple randomized design such that each sample is analyzed multiple times by XRF. Homogeneity may also be determined within sample using an applied version of ASTM E826. A single factor ANOVA is used to calculate uncertainty due to inhomogeneity ( $U_{hom}$ ). Uncertainty of the material is calculated by equation 2, where  $H=U_{hom}$ ,  $S$ = Standard deviation,  $t$ = t-value at 95% CI, and  $n$ = number of observations.

$$1. N_{MIN} = \max(10, \sqrt[3]{N_{PROD}}) \qquad 2. U_{CRM} = \frac{\sqrt{H^2 + S^2}}{\sqrt{n}} * t$$

**Certification Laboratories:** Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognized reference materials. Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

- LGC Standards - Manchester, NH
- Connecticut Metallurgical, Inc. - East Hartford, CT
- Dirats Laboratories - Westfield, MA
- IMR Test Labs - Lansing, NY
- NSL Analytical Services - Cleveland, OH
- SGS MSI - Melrose Park, IL
- AnchorCert Analytical - Birmingham, UK
- Applied Technical Services - Marietta, GA
- EAG Laboratories - Liverpool, NY
- Lithea s.r.o. - Brno-Sadová, Czech Republic
- New Hampshire Materials Laboratory - Somersworth, NH
- TEC Eurolab - Campogalliano, Italy
- Scrooby's Laboratory Services - Benoni, South Africa
- Universal Scientific Laboratory - Revesby, Australia

**Instructions for Use:** The test surface is on the opposite side of the labeled surface, which includes the material identification. This material is individually chill cast per piece. This manner of casting can cause the formation of inhomogeneous segregates in the upper, engraved portion of the disk. Therefore, the certification information above is not applicable to within 3mm of the engraved surface. Each packaged disk has been prepared by finishing the test surface using a lathe. The user must determine the correct surface preparation procedure for each analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing, as these processes may contaminate the surface. The minimum sample size for chips should be individually evaluated based on the analytical technique used; this would typically be greater than 0.1 grams. The material should be stored in a cool, dry location when not in use. Chips are not recommended for gas analysis.

**Period of Validity:** The certification of this material is valid indefinitely, within the uncertainty specified, provided the material is handled and stored in accordance with the instructions stated on this certificate. The certification is nullified if the material is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.

  
Kimberly Halkotis, Global Product Manager

March 1, 2022  
Certification Date



ISO 17034 Accredited: Reference Materials  
Producer, Certificate # 2848.02  
ISO/IEC 17025 Accredited: Chemical  
Testing, Certificate # 2848.01

**Conditions of Sale and Supply:** All CRMs & RMs sold are subject to applicable LGC Standard Terms and Conditions of Sale.



The following data represents all pertinent information reported as it applies to the chemical characterization of this material.

	Ag	Al	As	Au	Bi	Cd	Co	Cr	Cu	Fe	Ge	Mg	Mn
1	0.0120	0.00002	0.1600	0.0004	0.0160	0.0001	0.0012	0.00004	76.759	0.0002	0.0002	0.00004	0.0001
2	0.0120	0.0002	0.1620	0.0004	0.0186	0.0001	0.0013	0.0001	76.770	0.0005	0.0011	0.0003	0.0003
3	0.0126	0.0006	0.1640		0.0210	0.0001	0.0015	0.0001	76.993	0.0005		0.0010	0.0008
4	0.0130	0.0010	0.1670		0.0213	0.0002	0.0016	0.0002	77.280	0.0007		0.0090	<0.00005
5	0.0140	0.0030	0.1681		0.0219	0.0002	0.0017	0.0004	77.323	0.0008		0.0090	<0.0001
6	0.0155	0.0060	0.1700		0.0222	0.0002	0.0018	0.0007	77.550	0.0010		0.0132	<0.0002
7	0.0165	<0.00005	0.1720		0.0240	0.0004	0.0020	0.0010	77.625	0.0012		<0.00005	<0.001
8	0.0180	<0.001	0.1720		0.0250	0.0010	0.0020	<0.00005	77.780	0.0013		<0.0001	<0.001
9	0.0181	<0.0010	0.1738		0.0272	0.0015	0.0020	<0.001		0.0020		<0.0002	<0.001
10	0.0186	<0.0010	0.1740		0.0300	<0.0010	0.0021	<0.0010		<0.0010		<0.0010	<0.0010
11	0.0193	<0.002	0.1797		0.0308	<0.0010	0.0022	<0.0010		<0.002		<0.0010	<0.0010
12	0.0195	<0.002	0.1805		0.0320	<0.002	<0.002	<0.002		<0.002		<0.005	<0.002
13	0.0200	<0.002	0.1820		0.0340	<0.005	<0.002	<0.005		<0.005			<0.002
14	0.0200	<0.005	0.1870		0.0347		<0.005						<0.002
15	0.0210		0.1890		0.0387								<0.005
16	0.0220		0.1940										
17													
18													
Mean	0.0170	0.0018	0.1747	0.0004	0.0265	0.0004	0.0018	0.0004	77.260	0.0009	0.0007	0.0054	0.0004
STDV	0.0034	0.0023	0.0099		0.0066	0.0005	0.0003	0.0004	0.3881	0.0005	0.0006	0.0057	0.0004
<b>Certified</b>	<b>0.017</b>	<b>(0.002)</b>	<b>0.175</b>	<b>(&lt;0.0005)</b>	<b>0.026</b>	<b>0.0004</b>	<b>0.0018</b>	<b>0.0004</b>	<b>77.3</b>	<b>0.0009</b>	<b>(&lt;0.001)</b>	<b>(0.005)</b>	<b>(&lt;0.0004)</b>
U <sub>CRM</sub>	0.002		0.005		0.004	0.0004	0.0002	0.0003	0.3	0.0004			
Methods	I,IM,X,O,G	I,IM,O,X,G	I,IM,O,X,G	O,I	IM,I,O,X,G	IM,I,X,O	I,IM,X,O	IM,I,X,O,G	O,I,W,G,X	IM,I,X,O	O,X	I,IM,O,G,X	I,IM,O,X,G

	Nb	Ni	O	P	Pb	S	Sb	Se	Si	Sn	Zn	Zr
1	0.0001	0.0363	0.0060	0.0120	0.2010	0.0187	0.0410	0.0014	0.0002	20.891	0.0176	0.0001
2	0.0002	0.0378	0.0074	0.0130	0.2030	0.0207	0.0439	0.0015	0.0004	20.910	0.0178	0.0002
3	0.0003	0.0390		0.0130	0.2038	0.0210	0.0470	0.0020	0.0009	21.140	0.0179	0.0002
4	0.0003	0.0395		0.0139	0.2090	0.0211	0.0478	0.0020	0.0015	21.245	0.0180	0.0004
5	<0.00005	0.0397		0.0140	0.2100	0.0219	0.0480	0.0023	<0.0001	21.474	0.0180	<0.00005
6	<0.0001	0.0399		0.0140	0.2120	0.0220	0.0490	0.0026	<0.001	21.767	0.0180	<0.001
7	<0.0002	0.0410		0.0150	0.2140	0.0220	0.0490	0.0026	<0.001	21.770	0.0187	<0.001
8	<0.001	0.0420		0.0160	0.2140	0.0220	0.0500	0.0028	<0.001	21.780	0.0190	<0.0010
9	<0.0010	0.0424		0.0160	0.2180	0.0230	0.0500	0.0030	<0.0010	21.920	0.0190	<0.0010
10	<0.0010	0.0428		0.0160	0.2190	0.0231	0.0510	<0.002	<0.002	22.120	0.0190	<0.002
11	<0.002	0.0430		0.0160	0.2201	0.0233	0.0530	<0.005	<0.002	22.210	0.0195	<0.005
12	<0.005	0.0430		0.0163	0.2270	0.0233	0.0537	<0.0050	<0.002	22.289	0.0200	
13		0.0440		0.0167		0.0240	0.0569	<0.01	<0.005	22.540	0.0200	
14		0.0457		0.0215			0.0600	<0.01	<0.0050	22.650	0.0200	
15		0.0490		0.0220			0.0643				0.0202	
16		0.0510		0.0230								
17		0.0530		0.0246								
18		0.0547										
Mean	0.0002	0.0435	0.0067	0.0166	0.2126	0.0220	0.0510	0.0022	0.0007	21.765	0.0188	0.0002
STDV	0.0001	0.0052	0.0010	0.0038	0.0078	0.0014	0.0060	0.0006	0.0006	0.5716	0.0009	0.0001
<b>Certified</b>	<b>(0.0002)</b>	<b>0.044</b>	<b>(&lt;0.007)</b>	<b>0.017</b>	<b>0.213</b>	<b>0.0220</b>	<b>0.051</b>	<b>0.0022</b>	<b>(0.0007)</b>	<b>21.8</b>	<b>0.0188</b>	<b>(0.0002)</b>
U <sub>CRM</sub>		0.003		0.002	0.005	0.0009	0.003	0.0004		0.3	0.0006	
Methods	I,IM,X,O	I,O,IM,X,G	F	I,O,IM,X,W,G	O,I,IM,X	C,O,I,G,X	I,O,IM,X	I,IM,X,O,G	I,IM,O,X,W,G	I,O,W,G,X	I,IM,O,X	I,IM,X,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, IM=ICP-MS, D = DC Arc, O = AES, X = XRF, G = GDAES or GDMS, H = Hollow Cathode AES

