

Certified Reference Material **Certificate of Analysis**

Product ID: MBH-AL6063-20

ISO
17034:2016

ISO/IEC
17025:2017

ISO
9001:2015

Product Description: Aluminum Alloy, AA6063 / A96063

Description and Intended Use: This **Certified Reference Material** is covered under the scope of accreditation to **ISO 17034** by LGC Standards - Manchester, NH. As an ISO 17034 certified reference material, appropriate use of this material will fulfill the certified reference material and traceability requirements for use in **ISO 17025** accredited laboratories. This CRM may come in the form of a solid disk, or chips. The intended use of this CRM may include, but is not limited to, the calibration of instruments and the validation of analytical methods.

Certified Values listed in wt.% with associated uncertainties											
B	0.0011	± 0.0008	Co	0.0003	± 0.0002	Cr	0.0088	± 0.0006	Cu	0.030	± 0.001
Fe	0.156	± 0.004	Ga	0.0109	± 0.0006	Mg	0.481	± 0.008	Mn	0.023	± 0.001
Ni	0.0043	± 0.0004	Pb	0.0010	± 0.0004	Si	0.46	± 0.02	Ti	0.0107	± 0.0005
V	0.0115	± 0.0007	Zn	0.0064	± 0.0004	Zr	0.0011	± 0.0002			

Indicative Values listed in ppm							
Ag (1)	Al (98.8%)	As (<10)	Be (<1)	Bi (<20)	Ca (30)	Cd (<1)	
Li (10)	P (<50)	Sb (<10)	Sn (10)	Sr (<1)			

Homogeneity and Uncertainty: "Uncertainty" values, as reported adjacent to certified concentration values, are based on a 95% Confidence Interval. These estimated uncertainties include the combined effects of method imprecision, material inhomogeneity, and any bias between methods. Homogeneity data from experimental XRF results are reflected in both the overall statistics and certified data. Homogeneity samples are selected by a systematic sampling procedure. The number of samples may be determined by equation 1, where N_{prod} is the number of units produced and N_{min} is the number of samples used for homogeneity testing. These samples are arranged in a simple randomized design such that each sample is analyzed multiple times by XRF. Homogeneity may also be determined within sample using an applied version of ASTM E826. A single factor ANOVA is used to calculate uncertainty due to inhomogeneity (U_{hom}). Uncertainty of the material is calculated by equation 2, where $H=U_{hom}$, S = Standard deviation, t = t-value at 95% CI, and n = number of observations.

$$1. N_{MIN} = \max(10, \sqrt[3]{N_{PROD}})$$

$$2. U_{CRM} = \frac{\sqrt{H^2 + S^2}}{\sqrt{n}} * t$$

Certification Laboratories: Much of the analytical work performed to assess this material has been carried out by laboratories with proven competence, as indicated by their accreditation to ISO 17025. It is an implicit requirement for this accreditation that analytical work should be performed with due traceability, via an unbroken chain of comparisons, each with stated uncertainty, to primary standards such as the mole, or to nationally- or internationally-recognized reference materials. Of the individual results herein, some have traceability (to the mole) via primary analytical methods. Some are traceable to substances of known stoichiometry. Most have traceability via commercial solutions. Furthermore, some results have additional traceability to NIST standards, as part of the analytical calibration or process control.

- LGC Standards - Manchester, NH
- RSML - Bengaluru, India
- NSL Analytical Services - Cleveland, OH
- Laboratory Testing, Inc. - Hatfield, PA
- Connecticut Metallurgical, Inc. - East Hartford, CT
- IMR Test Labs - Lansing, NY
- SGS MSI - Melrose Park, IL
- Scooby's Laboratory Service - Rynfield, South Africa
- Applied Technical Services - Marietta, GA
- EAG Laboratories - Liverpool, NY
- AnchorCert Analytical - Birmingham, UK
- Luvac Inc. - Boylston, MA

Instructions for Use: The test surface is on the opposite side of the labeled surface, which includes the material identification. The entire thickness of the unit is certified. However, the user is cautioned not to measure disks less than 2 mm thick when using X-ray fluorescence spectrometry. Each packaged disk has been prepared by finishing the test surface using a lathe. The user must determine the correct surface preparation procedure for each analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing, as these processes may contaminate the surface. The minimum sample size for chips should be individually evaluated based on the analytical technique used; this would typically be greater than 0.1 grams. The material should be stored in a cool, dry location when not in use. Chips are not recommended for gas analysis.

Period of Validity: The certification of this material is valid indefinitely, within the uncertainty specified, provided the material is handled and stored in accordance with the instructions stated on this certificate. The certification is nullified if the material is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.


Kimberly Halkotis, Global Product Manager

October 7, 2021
Certification Date



ISO 17034 Accredited: Reference Materials
Producer, Certificate # 2848.02
ISO/IEC 17025 Accredited: Chemical
Testing, Certificate # 2848.01

Conditions of Sale and Supply: All CRMs & RMs sold are subject to applicable LGC Standard Terms and Conditions of Sale.



The following data represents all pertinent information reported as it applies to the chemical characterization of this material.

	Ag	Al	As	B	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Li
1	0.0001	98.770	0.00003	0.0001	0.00001	0.0017	0.0003	0.00002	0.0001	0.0070	0.0258	0.1440	0.0088	0.0001
2	0.0001	98.800	0.0005	0.0002	0.0001	0.0024	0.0007	0.00003	0.0001	0.0076	0.0260	0.1450	0.0105	0.0001
3	0.0001	98.800	<0.0001	0.0008	<0.0001	<0.0001	0.0007	0.0001	0.0002	0.0078	0.0278	0.1470	0.0105	0.0001
4	0.0003	98.810	<0.001	0.0008	<0.0001	<0.0001	0.0011	<0.0001	0.0002	0.0079	0.0280	0.1532	0.0107	0.0021
5	<0.0005		<0.001	0.0011	<0.0001	<0.001	0.0019	<0.0005	0.0005	0.0080	0.0280	0.1534	0.0109	<0.0001
6	<0.0005		<0.001	0.0022	<0.0005	<0.001	0.0050	<0.0005	0.0005	0.0086	0.0290	0.1539	0.0109	<0.0005
7	<0.001		<0.005	0.0022	<0.001	<0.001	0.0106	<0.001	0.0005	0.0086	0.0290	0.1550	0.0110	<0.001
8	<0.001			<0.0001	<0.001	<0.002	<0.0005	<0.001	<0.0005	0.0088	0.0292	0.1560	0.0110	
9				<0.001				<0.001	<0.0005	0.0090	0.0300	0.1562	0.0112	
10									<0.001	0.0090	0.0300	0.1570	0.0115	
11									<0.001	0.0092	0.0304	0.1570	0.0125	
12									<0.001	0.0096	0.0310	0.1600		
13										0.0100	0.0322	0.1617		
14										0.0100	0.0329	0.1655		
15										0.0110	0.0336	0.1680		
16											0.0340			
17														
18														
19														
20														
21														
Mean	0.0001	98.795	0.0003	0.0011	0.00003	0.0021	0.0029	0.0001	0.0003	0.0088	0.0298	0.1555	0.0109	0.0006
STDV	0.0001	0.0174	0.0003	0.0009	0.00003	0.0005	0.0037	0.00004	0.0002	0.0011	0.0025	0.0068	0.0009	0.0010
Certified	(0.0001)	(98.8)	(<0.001)	0.0011	(<0.0001)	(<0.002)	(0.003)	(<0.0001)	0.0003	0.0088	0.030	0.156	0.0109	(0.001)
U _{CRM}				0.0008					0.0002	0.0006	0.001	0.004	0.0006	
Methods	O,IM,I	O,I	O,IM,I	O,IM,I	O,IM,I	O,IM,I	O,IM,I	O,IM,I	O,I,IM	O,I,IM,X	O,I,IM,X	O,I,IM,X	O,IM,I,X	O,IM,I

	Mg	Mn	Ni	P	Pb	Sb	Si	Sn	Sr	Ti	V	Zn	Zr
1	0.4550	0.0195	0.0030	0.0015	0.0003	0.0010	0.3900	0.0002	0.0001	0.0097	0.0093	0.0050	0.0006
2	0.4570	0.0200	0.0036	0.0025	0.0005	<0.0005	0.4132	0.0007	0.0001	0.0100	0.0102	0.0055	0.0007
3	0.4680	0.0210	0.0037	0.0092	0.0009	<0.001	0.4370	0.0008	0.0002	0.0100	0.0106	0.0059	0.0010
4	0.4747	0.0213	0.0040	<0.0001	0.0010		0.4520	0.0010	<0.0001	0.0104	0.0107	0.0060	0.0010
5	0.4770	0.0219	0.0040	<0.002	0.0011		0.4620	0.0010	<0.0001	0.0104	0.0110	0.0060	0.0010
6	0.4780	0.0226	0.0042	<0.002	0.0014		0.4624	0.0012	<0.0005	0.0106	0.0110	0.0060	0.0013
7	0.4780	0.0229	0.0043	<0.005	0.0015		0.4670	0.0013	<0.0005	0.0106	0.0110	0.0061	0.0014
8	0.4819	0.0230	0.0044		0.0017		0.4700	0.0020	<0.001	0.0108	0.0111	0.0062	0.0014
9	0.4850	0.0231	0.0044		<0.005		0.4740	0.0023	<0.001	0.0110	0.0112	0.0064	0.0014
10	0.4850	0.0237	0.0045		<0.005		0.4830	0.0037	<0.01	0.0110	0.0119	0.0065	<0.001
11	0.4850	0.0240	0.0045				0.4950	<0.0005		0.0111	0.0119	0.0067	<0.002
12	0.4860	0.0244	0.0050				0.5179	<0.001		0.0113	0.0120	0.0070	
13	0.4962	0.0245	0.0050					<0.001		0.0115	0.0131	0.0073	
14	0.5000	0.0248	0.0050					<0.005		0.0119	0.0131	0.0074	
15	0.5068										0.0140	0.0074	
16													
17													
18													
19													
20													
21													
Mean	0.4809	0.0226	0.0043	0.0044	0.0010	0.0010	0.4603	0.0014	0.0001	0.0107	0.0115	0.0064	0.0011
STDV	0.0142	0.0017	0.0006	0.0042	0.0005		0.0346	0.0010	0.0001	0.0006	0.0012	0.0007	0.0003
Certified	0.481	0.023	0.0043	(<0.005)	0.0010	(<0.001)	0.46	(0.001)	(<0.0001)	0.0107	0.0115	0.0064	0.0011
U _{CRM}	0.008	0.001	0.0004		0.0004		0.02			0.0005	0.0007	0.0004	0.0002
Methods	O,I,IM,X	O,I,IM,X	O,IM,I,X	O,IM,I	O,IM,I	O,IM	O,I,IM	O,I,IM,X	O,IM,I	O,I,IM,X	O,I,IM,X	O,I,IM,X	O,IM,I

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, IM=ICP-MS, D = DC Arc, O = AES, X = XRF, G = GDAES or GDMS, H = Hollow Cathode AES

